

Performance you can trust

SAFE STEP® High Vis Tape

Part Code: 43540
Pack Size: 50mm wide x 18.25m long tape

No of Pages	02
Issue No	05
Date	04/21
Ref	SSNHVTD

Description

SAFE STEP® High Vis Tape provides a hard wearing and highly visible slip resistant surface. Ideal for marking out floors, entrance and exit points, walkways and stairs for example. For indoor applications to concrete, masonry, wood, ceramic tiles and metal etc

SAFE STEP® High Vis Tape is comprised of a mineral coated plastic film treated on one side with a pressure sensitive adhesive, protected by a removable liner.

Features

- Quick and easy to apply.
- Capable of withstanding temperature extremes.
- Durable anti-slip surface.
- Good resistance to water, motor oil, detergents, solvents and UV light.



Technical Data (Typical)

Colour:	Yellow	
Mineral Particles:	Aluminium Oxide	
Maximum Adhesive Bond Strength:	Over 48-72 hours	
Shelf Life:	2 years stored at 20-25°C in dry conditions	
Usable Temperature Range:	-40 to 90°C	
UV Resistance:	Good	
Minimum Application Temperature:	Above 5°C	
Chemical Resistance: (Incidental Contact)	Good resistance to water, motor oil, hydraulic fluid, detergent, petrol and diesel	
Suitable Application:	Internal applications only	
Pendulum slip Resistance using TRRL rubber (BS7976)	Result	Slip potential classification
Dry Pendulum Test Values (PTV)	86	(Low slip potential)*
Wet Pendulum Test Values (PTV)	73	(Low slip potential)*
Oily Pendulum Test Values (PTV)	68	(Low slip potential)*

*Potential to slip as interpreted in the guideline from UKSRG, 2011 recommended by the HSE

T +44 (0) 113 232 2600
F +44 (0) 113 232 2740
E customer-service@rocol.com
www.rocol.com

ROCOL House, Swillington, Leeds LS26 8BS

Registered Company No. 559693 VAT No. 742 0531 67
Registered Office: Admiral House, St Leonard's Road, Windsor, Berkshire SL4 3BL

ROCOL A division of **ITW** Ltd



BS EN ISO 9001
Certificate No. FM 12448



BS EN ISO 14001
Certificate No. EMS 67596



OHSAS 18001
Certificate No. OHS 78173



INVESTOR IN PEOPLE

Performance you can trust

Slip potential classification, based on pendulum test values (PTV)	PTV
High slip potential	0-24
Moderate slip potential	25-35
Low slip potential	36 +

Surface Preparation

All surfaces must be clean, dry and free from oil, grease, petrol, waxes and loosely adhered material prior to application of SAFE STEP® Tape.

Metal:

Rust and paint should be removed to ensure proper adhesion between the adhesive and the surface.

Wood:

Should be smooth, sound and dust free.

Concrete and Masonry:

Must be sound and non-crumbling, with no dust or grit present.

Application

Laying - remove the backing paper and accurately position the adhesive tapes. Start laying at one end and using firm pressure work towards the other end, without trapping air bubbles. A hard rubber or wooden roller may be of assistance. Should there be any trapped air bubbles, these can be punctured and pressed down.

Once the SAFE STEP® High Vis Tape is in place, it is immediately ready for use.

Applying SAFE STEP® High Vis Tape to Difficult Surfaces.

There are some surfaces to which it may be difficult to apply SAFE STEP® High Vis Tape or some that you may be unsure as to the compatibility. - For example, Alkyd or Epoxy resin coatings may have "waxy" ingredients which resist adhesives bonding them and some concretes may contain "anti-freeze" or silicone additives which may repel adhesives. Do not apply SAFE STEP® High Vis Tape to plasticised or vinyl floor coverings. When applying to quarry tiles do not apply over grout. Apply SAFE STEP® Tapes over the quarry tile surface only. Not suitable for very porous surfaces.

As there are so many variables it is impossible to legislate for every eventuality but as a rule of thumb, **IF YOU ARE UNSURE, TEST IT!**

Test Patch

Apply a piece of SAFE STEP® Tape to a clean, dry surface in a normal traffic area and leave for a minimum of 7 days. If after this time it is still securely applied, the surface should be satisfactorily compatible.

Surface Maintenance

It is essential that SAFE STEP® High Vis Tape is cleaned regularly to maximise anti-slip performance. Under normal conditions periodically sweeping with a stiff brush is all that should be required. For heavily soiled surfaces the use of a water based biodegradable detergent cleaner may be used in conjunction with a fibre bristled brush. After cleaning, rinse thoroughly with clean water and allow to dry before use.

Disclaimer: The information in this publication is based on our experience and reports from customers. There are many factors outside our control or knowledge which may affect the use and performance of our products, for this reason it is given without responsibility.

T +44 (0) 113 232 2600
F +44 (0) 113 232 2740
E customer-service@rocol.com
www.rocol.com

ROCOL House, Swillington, Leeds LS26 8BS

Registered Company No. 559693 VAT No. 742 0531 67
Registered Office: Admiral House, St Leonard's Road, Windsor, Berkshire SL4 3BL

ROCOL A division of ITW Ltd



BS EN ISO 9001
Certificate No. FM 12448



BS EN ISO 14001
Certificate No. EMS 67596



OHSAS 18001
Certificate No. OHS 78173



INVESTOR IN PEOPLE